

Bisphenol-A type liquid epoxy resin E-51 is an unmodified liquid epoxy resin with medium viscosity produced from bisphenol-A and epichlorohydrin. This is a standard liquid epoxy resin and a wide variety of curing agents are available to cure this liquid epoxy resin at ambient conditions and also at elevated temperature. When cured with appropriate hardener, E-51 gives excellent mechanical, chemical, electrical and adhesion properties. Because of these properties it finds use in various applications.

- Solvent based, high solid content and solvent-free coatings
- Adhesives
- Civil and construction engineering industry
- Automotive coatings
- Can & coil coatings
- Marine and industrial protective coatings
- Tooling, potting, casting and molding compounds
- Composites
- Stabilizer in PVC

Appearance	Visual	Transparent, colorless to light yellow liquid
Color	ASTM D 1544-04	0.5Gmax
Epoxy equivalent	ASTM D 1652-04	178-200
Viscosity (25 °C)	ASTM D 2196-05	8000-17000cP
Hydrolyzed chlorine	ASTM D 1726-03	0.05%max

Epoxy value	ASTM D 1652-04	5.12-5.40
Density (25 °C)	ASTM D 1475-98	1.16g/ml
Water content	ASTM E 203-01	0.05%max
ECH content	TEC-AS-P-023	10ppm max
Flash point	ASTM D 93	253

**4.**

This product is packed and transported in 220kg sealed iron drum.

Other packaging can be provided on request.

- 1). Epoxy resin should be stored in a cool and dry place, avoid rain and sun exposure.
- 2). When deploying epoxy resin, it is necessary to use it now and mix the curing agent in proper proportion to avoid waste.
- 3). Epoxy resin storage life is generally 1 year, beyond the time limit should be tested, meet the index can still be used.

All recommendations for use of our products whether given by us in writing, verbally or to be implied from the results of tests carried out by us are based on the current state of our knowledge. Although, the information contained in this sheet is accurate, no liability can be accepted in respect of such information. We warrant only that our product will meet the designated specifications and make no other warranty either express or implied, including any warranty of merchantability or fitness for a particular.